

# Weathered Red

Extruded wirecut bricks with a weathered finish, Weathered Reds are a popular facing material. Their uniform appearance makes them a favourite for new builds and extensions, especially in the Midlands and the North, where their colour closely matches much of the existing housing stock. The manufacturing process sees them tinted to appear they been exposed to decades of natural weathering.

## FIND OUT MORE ABOUT OUR BRICK RANGE

T: 0161 641 3579

W: [www.manchesterbrick.com](http://www.manchesterbrick.com)



### PRODUCT TECHNICAL INFORMATION

MANCHESTER BRICK CODE	MBS01300
PRODUCTION PLANT	BS EN 771-1
CONFIGURATION	Vertically Perforated 26% Voids
COLOUR	Red / Black
APPEARANCE	Smooth
SIZE Metric	65mm x 215mm x 102.5mm 73mm x 215mm x 102.5mm
PACK SIZE	464 / 512
INDIVIDUAL DRY BRICK WEIGHT	2.4kg / 2.6kg

### TECHNICAL PROPERTIES TO BS EN 771-1

TYPE	Wirecut
GROSS DRY DENSITY (KG/M <sup>3</sup> /TOLERANCE)	2300kg/m <sup>3</sup> (D1)
ACTIVE SOLUBLE SALTS	S2
COMPRESSIVE STRENGTH	>90N/mm <sup>2</sup>
THERMAL CONDUCTIVITY*	≤0.47 W/m.k
SIZE TOLERANCE (MEAN/RANGE)	T2/R2
DURABILITY DESIGNATION	F2
WATER ABSORPTION	≤8%/md
INITIAL RATE OF WATER ABSORPTION (KG/(M <sup>2</sup> MIN))	1.0 - 4.0kg/m <sup>2</sup> .min (IW3)
REACTION TO FIRE	A1



Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Manchester Brick Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.

