Adlington Multi

FIND OUT MORE ABOUT OUR BRICK RANGE

T: 0161 641 3579

W: www.manchesterbrick.com



PRODUCT TECHNICAL INFORMATION	
MBS02420	
BS EN 771-1	
Vertically Perforated 26% Voids	
Grey Multi	
Sandfaced	
215mm x 102.5mm x 65mm	
512	
2.4kg	

TECHNICAL PROPERTIES TO BS EN 771-1	
ТҮРЕ	Wirecut
GROSS DRY DENSITY (KG/M³/TOLERANCE)	2300 (D1)
ACTIVE SOLUBLE SALTS	S2
COMPRESSIVE STRENGTH	\geq 75N/mm ²
THERMAL CONDUCTIVITY*	-0.47 W/m.k
SIZE TOLERANCE (MEAN/RANGE)	T2/R2
DURABILITY DESIGNATION	F2
WATER ABSORPTION	≤7%m/md
INITIAL RATE OF WATER ABSORPTION (KG/(M² MIN))	1.0-4.0
REACTION TO FIRE	A1



guidance only. Any questions regarding this data should be referred to the Manchester Brick Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.







