## Collyhurst Yellow

## FIND OUT MORE ABOUT OUR BRICK RANGE

T: 0161 641 3579

W: www.manchesterbrick.com



PRODUCT TECHNICAL INFORMATION	
MANCHESTER BRICK CODE	MBS02720
MANUFACTURED TO	BS EN 771-1
CONFIGURATION	Vertically Perforated Voids
COLOUR	Buff/Black Spots
APPEARANCE	Dragfaced/Textured
SIZE Metric	215mm x 102.5mm x 65mm
PACK SIZE	520
INDIVIDUAL DRY BRICK WEIGHT	2.1kg

TECHNICAL PROPERTIES TO BS EN 771-1		
ТҮРЕ	Wirecut	
GROSS DRY DENSITY (KG/M³ /TOLERANCE)	2200 ±10%	
ACTIVE SOLUBLE SALTS	S2	
COMPRESSIVE STRENGTH	$\geq$ 40N/mm <sup>2</sup>	
THERMAL CONDUCTIVITY*	0.36 W/m.k	
SIZE TOLERANCE (MEAN/RANGE)	T2/R1	
DURABILITY DESIGNATION	F2	
WATER ABSORPTION	<7%	
INITIAL RATE OF WATER ABSORPTION (KG/(M² MIN))	≤0.8	
REACTION TO FIRE	A1	



Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Manchester Brick Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.







