Smooth Buff

FIND OUT MORE ABOUT OUR BRICK RANGE

T: 0161 641 3579

W: www.manchesterbrick.com



PRODUCT TECHNICAL INFORMATION	
MBS02560	
BS EN 771-1	
Vertically Perforated Voids	
Buff	
Smooth	
215mm x 102.5mm x 65mm	
520	
2.1kg	

TECHNICAL PROPERTIES TO BS EN 771-1	
ТҮРЕ	Wirecut
GROSS DRY DENSITY (KG/M³/TOLERANCE)	2200 ±10%
ACTIVE SOLUBLE SALTS	S2
COMPRESSIVE STRENGTH	\geq 75N/mm ²
THERMAL CONDUCTIVITY*	0.36 W/m.k
SIZE TOLERANCE (MEAN/RANGE)	T2/R2
DURABILITY DESIGNATION	F2
WATER ABSORPTION	<7%
INITIAL RATE OF WATER ABSORPTION (KG/(M² MIN))	≤0.8
REACTION TO FIRE	A1



Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Manchester Brick Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.







