

Calderwood Claret

FIND OUT MORE ABOUT OUR BRICK RANGE

T: 0161 641 3579

W: www.manchesterbrick.com



PRODUCT TECHNICAL INFORMATION

MANCHESTER BRICK CODE	MBS03000
MANUFACTURED TO	BS EN 771-1
CONFIGURATION	Vertically Perforated Voids
COLOUR	Red Multi
APPEARANCE	Rusticated
SIZE Metric	215mm x 102.5mm x 65mm
PACK SIZE	400
INDIVIDUAL DRY BRICK WEIGHT	2.1kg

TECHNICAL PROPERTIES TO BS EN 771-1

TYPE	Wirecut
GROSS DRY DENSITY (KG/M ³ /TOLERANCE)	1480kg/m ³ (D1)
ACTIVE SOLUBLE SALTS	S2
COMPRESSIVE STRENGTH	≥40N/mm ²
THERMAL CONDUCTIVITY*	P=90% 0.69 W/m.k
SIZE TOLERANCE (MEAN/RANGE)	T2/R1
DURABILITY DESIGNATION	F2
WATER ABSORPTION	≤12% m/md
INITIAL RATE OF WATER ABSORPTION (KG/(M ² MIN))	1.0- 2.2kg/m ² .min (IW3)
REACTION TO FIRE	A1



Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Manchester Brick Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.

